

**PEACOCK LABORATORIES, INC.**  
1901 S. 54th Street  
Philadelphia, PA 19143

**PEACOCK #145 ACID-RESISTANT MIRRO-BOND BLACK/WHITE:**

**APPLICATION:**

Peacock #145 acid resistant mirro bond is available in black or white, and satin or matte finishes. It can be applied directly over silver or galvanic copper. When silk screened over silver, it will resist silver strip or acid for wash out techniques used in decorative silvering. Acid resist can be used for creating a two tone metal finish by selectively anodizing or buffing aluminum or brass parts and then stripping off the Peacock #145 with #281 mirro-backing thinner. Reduce with #281 mirro-backing thinner. Apply a minimum of two coats.

**FEATURES:**

UV resistance

Acid Resistance

Excellent Opacity

Dry to the touch and for recoat in 20 minutes, acid resistant in one hour, full hardness in 24 hours.

**PRINCIPAL USES:**

Mirror backing.

Resists silver strip or acid for wash out techniques used in decorative silvering.

Metal protection.

Creating two tone metal finish via selective anodizing or buffing

**APPEARANCE:**

Black or white, satin or matte finish.

**OPACITY:**

Excellent.

**DRYING:**

Air Dry: Dry to touch and for recoat in 15 to 20 minutes. Acid resistance after one hour. Full hardness in 24 hours. Minimum two coats are recommended.

**WASH-UP:**

Peacock MIRRO-BACKING thinner #281

**THINNERS AND ADDITIVES:**

Peacock MIRRO-BACKING thinner #281

**COVERAGE:**

Approximately 400 square feet per gallon.

**MIXING INSTRUCTIONS:**

Peacock #145 may be mixed four parts to one with #281 thinner.

Pot life is 1 hour

**REMARKS:**

Shelf life of Peacock #145 is 2 years. Product should be shaken before use, especially after extended storage. Always pretest for chemical resistance or specific conditions.

**Disclaimer**

- 1) All products are sold without warranty of any kind and purchaser will, by their own test, determine the suitability of such products for their own use.
- 2) Products are for commercial use only and may contain hazardous materials.
- 3) It is the responsibility of the user to determine local restrictions on the use and disposal of products.
- 4) All claims must be made within ten days of receipt of goods. No returns accepted without our written consent. There is a 20% restocking fee on returnable items.
- 5) All orders subject to change in price without notice according to price and availability of materials at time of shipment.